



Mix with water.



Mix with approximately 200 grams of

water per 1 kg of quick cement.



Average setting time (at 22°C and relative humidity at 60%) 2 to 4 minutes.



Use at ambient temperatures between 5°C and 30°C.



Keep in a dry and ventilated place. The product, sealed in the original package keeps for a period of one year.



Keep in a dry and ventilated place. The product, sealed in the original package keeps for a period of one year.



Hydraulic binder consisting of special quick setting cement and fine selected sands.

Exterior and interior restoration of small portions of plaster. Ideal for the quick installation of electrical boxes and tubes, clamps, windows and doors, dowels and wooden or metal frames.

Quick setting cement binder

CICLO: The substrate where Cemento rapido in sacchetto is applied, must be stable (not subject to hygrometric shrinkage or to detachment of loose parts), free of dust, salts, greasy or oily substances. Wet the surface thoroughly before application.

Cemento rapido in sacchetto must be applied quickly, in a time that does not exceed 2 minutes. If the mixture starts the hardening phase, no more water must be added, so mix small quantities of Cemento rapido in sacchetto at a time.

Rev.: 4.0 - 14/12/2021





8012760984027 2000 g

8012760984225 5000 g

WARNINGS: Mix the product with an indicated quantity of water and do not add any more to restore the workability after it has started to set. During the summer, use fresh water to mix and do not expose the sacks to the sun before using them. In the winter, use water at about 15 to 20°C. Do not apply to substrates that are frozen, thawing or with frost risk in the 24 hours after applying. Using an excessive amount of mixing water determines the reduction of mechanical strength and the increase in hydraulic shrinkage of the hardened mortar. The product is ready to use and should be mixed only with potable water. The addition of foreign matter may compromise the technical-applicative characteristics.

FORMATS AVAILABLE	DIMENSIONS P x L x H (mm)	PCS. X IMB.	LAYERS P.	X LAYER	X PALLET
2000 g		10	3	60	180
5000 g		4	3	24	72